

TECHNICAL DATA SHEET

KEXCELLED THE K6™ PLA FR

Product code:	Revision Number:	Revision date:	TDS No.:
THE K6™ PLA FR	04	12/01/2022	KT011

Characteristic:

Environmentally friendly|good interlayer bond|no buckling deformation.

IDENTIFICATION OF THE MATERIAL

Trade name	THE K6™ PLA FR
Chemical name	Polylactic Acid
Use	3D Printing
Origin	KEXCELLED

GUIDELINE FOR PRINT SETTINGS

Nozzle temperature	210~230℃
Bed temperature	30~60℃
Bed modification	Tape or glue below 60℃
Active cooling fan	ON,50%~100%
Layer height	0.2mm
Shell thickness	≥0.8mm
Print speed	40-80mm/s

Settings are based on a 0.4mm nozzle.

MATERIAL PROPERTIES

		Test Method
Melt temperature	~160℃	ISO 11357
Glass transition temperature	~60℃	ISO 11357
Melt flow rate (MFR) ¹	7~10 g/10min	ISO 1133
Heat deflection temperature(HDT) ²	55℃	ISO 75
Vicat softening temperature(VST) ³	57℃	ISO 306
Density	1.28~1.30g/cm ³	ISO 1183
Odor	Odorless	/
Solubility	Insoluble in water	/

1.test conditions: T= 190℃; m= 2.16kg.

2. test conditions:0.45MPa;120℃/h.

3. test conditions:10N; 120℃/h.

MECHANICAL PROPERTIES|TENSILE TEST
Test Method ISO 527

All test specimens were printed using an FlashForge Guider 2s under the following conditions:

Printing temperature: 210°C

Heated bed temperature: 60°C

Print speed: 50mm/s

Shell thickness: 1.2mm

Infill under 45°




Printed horizontal X,Y-axis

Infill	100%
Tensile strength (Mpa)	35~40
Elongation at break (%)	2~4
Emodulus (Mpa)	4100~4600

MECHANICAL PROPERTIES|IMPACT TEST
Test Method ISO 179

The same conditions as tensile test.

1→impact direction




Infill	100%
Impact strength (KJ/m ²)	34~40
Notch impact strength ¹ (KJ/m ²)	6~8

MECHANICAL PROPERTIES |FLEXURAL TEST
Test Method ISO 178

The same conditions as tensile test.

1→bending direction



Infill	100%
Maximum force (Mpa)	60~65
Flexural modulus (Mpa)	1800~2000

1. notch type: type A

FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Diameter 2.85mm	2.85±0.03mm	EX1125
Diameter 3.00mm	3.00±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Max roundness deviation (2.85)	0.03mm	EX1125
Max roundness deviation (3.00)	0.03mm	EX1125
Net weight on reel	1kg	EX1125