

TECHNICAL DATA SHEET

KEXCELLED THE K5™ COFFEE

Product code:	Revision Number:	Revision date:	TDS No.:
THE K5™ COFFEE	01	28/11/2025	KT111

Characteristic:

Environmentally friendly | Frosted texture | Aroma of coffee.

IDENTIFICATION OF THE MATERIAL

Trade name	THE K5™ COFFEE
Chemical name	Polylactic Acid
Use	3D Printing
Origin	KEXCELLED

GUIDELINE FOR PRINT SETTINGS

Nozzle temperature	200~240°C
Bed temperature	35~55°C
Bed modification	PEI frosted board
Active cooling fan	ON,50%~100%
Layer height	0.2mm
Shell thickness	≥0.8mm
Print speed	≤250mm/s

Settings are based on a 0.4mm nozzle.

MATERIAL PROPERTIES

		Test Method
Melt temperature	~165°C	ISO 11357
Glass transition temperature	~60°C	ISO 11357
Melt flow rate (MFR)¹	2~8g/10min	ISO 1133
Heat deflection temperature(HDT)²	52°C	ISO 75
Vicat softening temperature(VST)³	73°C	ISO 306
density	1.41±0.02g/cm ³	ISO 1183
Odor	COFFEE	/
Solubility	Insoluble in water	/

1. test conditions: T= 190°C; m= 2.16kg.


2. test conditions:0.45MPa;120°C/h.

3. test conditions:10N; 120°C/h.

MECHANICAL PROPERTIES|TENSILE TEST **Test Method ISO 527**

All test specimens were printed using a BambuLab X1C under the following conditions:


- Printing temperature: 220°C
- Heated bed temperature: 55°C
- Print speed: 262.5mm/s
- Shell thickness: 1.2mm
- Infill under 45°



Infill	100%	100%	100%
Tensile strength (Mpa)	23~28	25~30	10~15
Elongation at break (%)	8~15	10~15	1~5
Emodulus (Mpa)	1400~2000	1600~1900	1000~2000

MECHANICAL PROPERTIES|IMPACT TEST **Test Method ISO 179**


The same conditions as tensile test.



Infill	100%	100%	100%
Impact strength (KJ/m ²)	20~30	25~35	4~8
Notch impact strength ³ (KJ/m ²)	5~10	8~15	1~3

MECHANICAL PROPERTIES |FLEXURAL TEST **Test Method ISO 178**

The same conditions as tensile test.



Infill	100%	100%	100%
Maximum force (Mpa)	40~50	50~60	18~25
Flexural modulus (Mpa)	1800~2500	2100~2500	1100~1500

1. Z,X-axis test data are for reference only
2. the stress range of the Z,X-axis modulus: 10~20MPa
3. notch type: type A

FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Net weight on reel	1kg	EX1125